## SHOWA KAKO CORPORATION

Head Office: 18-23, Yoshino-Cho, Suita-City, Osaka

564-0054, Japan

Phone: +81-6-6384-1501 Fax: +81-6-6384-2287

## **Quality Specifications**

## **Product**: Stannic oxide

Grade	_
Chemical name	Stannic oxide
CAS No.	18282-10-5
Chemical formula	SnO <sub>2</sub>
M.W.	150.7

## [ Requirements ]

Test Item	Specification	Test method
Appearance	Pale yellowish powder	Visual test
Chloride (as Cl)	0.05% max.	Ion chromatography
Sulfate (as SO <sub>4</sub> )	0.05% max.	Ion chromatography
Nitrate (as NO <sub>3</sub> )	0.05% max.	Ion chromatography
Heavy metals (Oxides)	0.03% max.	Atomic absorption spectrometry
Iron (as Fe <sub>2</sub> O <sub>3</sub> )	0.20% max.	Atomic absorption spectrometry
Ignition loss	0.60% max.	550 ± 50 °C, 3 hours
Assay	99.0% min.	100-(Heavy metals+ Iron+ Ignition loss) (%)